See discussions, stats, and author profiles for this publication at: https://www.researchgate.net/publication/386903225

Degradation of Polypropylene Random Copolymer in Aqueous Solution of Chlorine Dioxide: Effect of Crystalline Structure and Morphology

Preprint · December 2024

citations 0 READS

2 authors, including:

Rohollah Shamizade Sharif University of Technology 7 PUBLICATIONS 2 CITATIONS

SEE PROFILE

Degradation of Polypropylene Random Copolymer in Aqueous Solution of Chlorine Dioxide: Effect of Crystalline Structure and Morphology

R. Shamizadeh¹, G. Pircheraghi¹

Polymeric Materials Research Group (PMRG), Department of Materials Science and Engineering, Sharif University of Technology, 11365-9466 Tehran, Iran

Abstract

The effect of different crystalline phases and spherulite diameter (D_s) on polypropylene random copolymer (PP-R) aging behavior in chlorine dioxide (ClO₂) was investigated. Three samples were prepared, a sample without a nucleating agent (P) and two samples containing α (A) and β (B) phase nucleating agents. The aging process was conducted in 20 ppm ClO₂ aqueous solution at 60 °C for up to 1440 h. For initial (unaged) samples, X-ray Diffraction (XRD) and Optical Microscope (OM) analysis showed that they were composed of different crystalline phases (P: $\alpha + \gamma + \beta$, A: γ $+\alpha$, and B: $\beta + \alpha$) and different D_s (P>B>A). The extent of chemical degradation was monitored by Carbonyl Index (CI) obtained from Fourier Transform Infrared Spectroscopy (FTIR). After 1440 h of aging, A sample had the highest, and P sample had the lowest CI values. Elongation at break (ε_b) values from a tensile test showed that A and B samples reached 50% of their initial ε_b after 700 and 800 h, respectively. In contrast, ε_b for P decreased only 25% after 1440 h pointing out the less chain scission and degradation. Rheological experiments and isothermal and nonisothermal Differential Scanning Calorimetry (DSC) were conducted to study the characteristics of degraded chains in melt state and their crystallization behavior, respectively. Finally, summarizing the test data concluded that the spherulite size controls the chemical stability of PP-R in water containing ClO₂, and samples with smaller spherulite sizes are more susceptible to chemical degradation.

Keywords: Polypropylene random copolymer, Crystalline Structure, Morphology, Spherulite size, Chemical Degradation, Chlorine Dioxide

Graphical Abstract



1. Introduction

The chemical degradation of polypropylene random copolymer (PP-R) in chlorinated water presents a critical challenge for manufacturers and users of plastic piping systems, as it directly impacts the longevity and safety of water infrastructure [1], [2]. While PP-R has become the material of choice for hot and cold water distribution networks due to its excellent thermal stability and mechanical properties [3], its susceptibility to oxidative degradation when exposed to disinfectants like chlorine dioxide and sodium hypochlorite threatens its long-term performance [4]. This vulnerability is particularly concerning given that water disinfection is essential for preventing waterborne diseases [5], creating an unavoidable tension between maintaining water safety and preserving pipe integrity. Understanding the degradation mechanisms and developing strategies to enhance PP-R's resistance to chlorinated water is therefore crucial for ensuring the reliability of modern plumbing systems [6].

Previous researches has extensively documented the general degradation behavior of PP-R in chlorinated water environments. Studies have shown that exposure to chlorine-based disinfectants leads to chain scission, reduction in molecular weight, and eventual embrittlement of the polymer [7], [8], [9]. Multiple analytical approaches have been employed to track this degradation process: infrared microscopy has revealed the spatial distribution of oxidation products and antioxidant depletion across pipe walls [4], while rheological measurements have demonstrated significant changes in molecular weight distribution and melt behavior [10], [11]. Time-resolved studies have shown that the degradation progresses from the pipe surface inward, with a complex interplay between diffusion and reaction kinetics [12]. However, these investigations have primarily focused

on bulk property changes without considering the fundamental role of polymer microstructure in the degradation mechanism.

The crystalline structure of PP-R, which can exist in multiple polymorphic forms (α , β , and γ), significantly influences its mechanical and thermal properties [13]. The α -form, characterized by a monoclinic unit cell, is the most common structure, while the β -form with its hexagonal arrangement offers improved impact strength and toughness [14], [15]. The γ -form, typically induced under high pressure or in copolymers, exhibits unique chain packing that affects mechanical properties [16], [17]. Recent studies have demonstrated that β -nucleated PP-R exhibits enhanced mechanical properties and thermal stability compared to conventional α -form materials [7], [18]. The morphological characteristics of these different forms, including spherulite size and lamellae arrangement, can be controlled through nucleating agents and processing conditions [19], [20]. Nevertheless, the relationship between these different crystalline forms and their resistance to chemical degradation by chlorine dioxide remains largely unexplored. This gap is particularly significant given that chlorine dioxide's degradation mechanism may differ from other oxidizing agents due to its unique molecular structure and reactivity [21], [22].

Furthermore, while the importance of polymer morphology in photooxidative and thermal degradation has been established [15], [23], [24], [25], [26], [27], [28], [29], [30], [31], its role in chemical degradation by chlorine dioxide is not well understood. The complex hierarchical structure of PP-R, from molecular to macroscopic scales, includes various interfaces between crystalline and amorphous regions that could influence degradation patterns [32], [33]. Studies on other degradation modes have shown that the initial attack often occurs in the amorphous regions, followed by progressive deterioration of the crystalline domains [34], [35]. The spherulitic

structure's role in degradation has been particularly highlighted in thermal oxidation studies, where the spherulite boundaries act as preferred oxidation sites [28]. However, the specific influence of morphological parameters such as crystallite size, lamellae thickness, and amorphous region distribution on chlorine dioxide-induced degradation remains unclear. Advances in understanding polymer oxidation mechanisms [36], [37] suggest that the spatial arrangement of crystalline and amorphous regions could significantly affect both the diffusion pathways and reaction kinetics of oxidizing species. The lack of comprehensive studies connecting crystalline structure, morphology, and degradation kinetics has limited our ability to design more resistant PP-R materials for water distribution applications.

To address these knowledge gaps regarding the influence of crystalline structure and morphology on PP-R degradation in chlorine dioxide environments, we designed a comparative study using three PP-R formulations: one without nucleating agents and two containing α and β phase nucleating agents, respectively. Through controlled exposure to 20 ppm chlorine dioxide solution at 60°C, we systematically investigated how different crystalline phases (α , β , and γ) and spherulite sizes affect the degradation process. Our analysis focused on two primary outcomes: (1) establishing the relationship between initial crystalline structure/morphology and degradation resistance through combined XRD and POM analysis, and (2) determining the mechanistic pathway of degradation in different crystalline phases through correlation of chemical (FTIR), mechanical (tensile), thermal, and rheological measurements. This approach directly addresses the identified gap in understanding how polymer microstructure influences chlorine dioxide-induced degradation, providing insights essential for developing more resistant PP-R materials.

Reference

- J. Fischer, P. Freudenthaler, R. Lang, W. Buchberger, and S. Mantell, "Chlorinated Water Induced Aging of Pipe Grade Polypropylene Random Copolymers," *Polymers*, vol. 11, no. 6, p. 996, Jun. 2019, doi: 10.3390/polym11060996.
- [2] A. Vertova *et al.*, "Chlorine Dioxide Degradation Issues on Metal and Plastic Water Pipes Tested in Parallel in a Semi-Closed System," *IJERPH*, vol. 16, no. 22, p. 4582, Nov. 2019, doi: 10.3390/ijerph16224582.
- [3] L. Yu, T. Wu, T. Chen, F. Yang, and M. Xiang, "Polypropylene random copolymer in pipe application: Performance improvement with controlled molecular weight distribution," *Thermochimica Acta*, vol. 578, pp. 43–52, Feb. 2014, doi: 10.1016/j.tca.2013.11.009.
- [4] S. Damodaran *et al.*, "Monitoring the effect of chlorine on the ageing of polypropylene pipes by infrared microscopy," *Polymer Degradation and Stability*, vol. 111, pp. 7–19, Jan. 2015, doi: 10.1016/j.polymdegradstab.2014.10.006.
- [5] A. A. Lanrewaju, A. M. Enitan-Folami, S. Sabiu, and F. M. Swalaha, "A review on disinfection methods for inactivation of waterborne viruses," *Front. Microbiol.*, vol. 13, p. 991856, Sep. 2022, doi: 10.3389/fmicb.2022.991856.
- [6] E. Blázquez-Blázquez, J. Lahoz, E. Pérez, and M. L. Cerrada, "An effective package of antioxidants for avoiding premature failure in polypropylene random copolymer plastic pipes under hydrostatic pressure and high temperature," *Polymers*, vol. 13, no. 16, p. 2825, 2021.
- [7] J. Fischer, R. Lang, P. Bradler, P. Freudenthaler, W. Buchberger, and S. Mantell, "Global and Local Aging in Differently Stabilized Polypropylenes Exposed to Hot Chlorinated

Water with and without Superimposed Mechanical-Environmental Loads," *Polymers*, vol. 11, no. 7, p. 1165, Jul. 2019, doi: 10.3390/polym11071165.

- [8] I. A. Khan, K. H. Lee, Y.-S. Lee, and J.-O. Kim, "Degradation analysis of polymeric pipe materials used for water supply systems under various disinfectant conditions," *Chemosphere*, vol. 291, p. 132669, 2022.
- [9] N. B. Samarth and P. A. Mahanwar, "Degradation of Polymer & amp; Elastomer Exposed to Chlorinated Water—A Review," *OJOPM*, vol. 11, no. 01, pp. 1–50, 2021, doi: 10.4236/ojopm.2021.111001.
- [10] H. Azizi, I. Ghasemi, and M. Karrabi, "Controlled-peroxide degradation of polypropylene: Rheological properties and prediction of MWD from rheological data," *Polymer Testing*, vol. 27, no. 5, pp. 548–554, Aug. 2008, doi: 10.1016/j.polymertesting.2008.02.004.
- [11] K. Bernreitner, W. Neiβl, and M. Gahleitner, "Correlation between molecular structure and rheological behaviour of polypropylene," *Polymer Testing*, vol. 11, no. 2, pp. 89–100, 1992, doi: 10.1016/0142-9418(92)90040-I.
- [12] V. P. Kelkar, C. B. Rolsky, A. Pant, M. D. Green, S. Tongay, and R. U. Halden, "Chemical and physical changes of microplastics during sterilization by chlorination," *Water research*, vol. 163, p. 114871, 2019.
- [13] M. Gahleitner, C. Grein, S. Kheirandish, and J. Wolfschwenger, "Nucleation of Polypropylene Homo- and Copolymers," *International Polymer Processing*, vol. 26, no. 1, pp. 2–20, Mar. 2011, doi: 10.3139/217.2411.
- [14] F. Luo *et al.*, "New Understanding in Tuning Toughness of β-Polypropylene: The Role of β-Nucleated Crystalline Morphology," *Macromolecules*, vol. 42, pp. 9325–9331, 2009, doi: 10.1021/MA901651F.

- [15] H. Wu, Y. Zhao, X. Dong, L. Su, K. Wang, and D. Wang, "Probing into the microstructural evolution of isotactic polypropylene during photo-oxidation degradation," *Polymer Degradation and Stability*, vol. 183, p. 109434, Jan. 2021, doi: 10.1016/j.polymdegradstab.2020.109434.
- [16] I. L. Hosier, R. G. Alamo, P. Esteso, J. R. Isasi, and L. Mandelkern, "Formation of the α and γ Polymorphs in Random Metallocene–Propylene Copolymers. Effect of Concentration and Type of Comonomer," *Macromolecules*, vol. 36, no. 15, pp. 5623–5636, Jul. 2003, doi: 10.1021/ma030157m.
- [17] B. Lotz, S. Graff, C. Straupé, and J. C. Wittmann, "Single crystals of γ phase isotactic polypropylene: combined diffraction and morphological support for a structure with nonparallel chains," *Polymer*, vol. 32, no. 16, pp. 2902–2910, Jan. 1991, doi: 10.1016/0032-3861(91)90185-L.
- [18] L. Liu, Y. Zhao, C. Zhang, Z. Dong, K. Wang, and D. Wang, "Morphological Characteristics of β-Nucleating Agents Governing the Formation of the Crystalline Structure of Isotactic Polypropylene," *Macromolecules*, vol. 54, no. 14, pp. 6824–6834, Jul. 2021, doi: 10.1021/acs.macromol.1c01038.
- [19] J. Fan and J. Feng, "Study on β-nucleated controlled-rheological polypropylene random copolymer: crystallization behavior and a possible degradation mechanism," *Industrial & Engineering Chemistry Research*, vol. 52, no. 2, pp. 761–770, 2013.
- [20] J. Cao and Q.-F. Lü, "Crystalline structure, morphology and mechanical properties of β-nucleated controlled-rheology polypropylene random copolymers," *Polymer testing*, vol. 30, no. 8, pp. 899–906, 2011.

- [21] U. Haida Nadia Mohamed Jefri *et al.*, "A systematic review on chlorine dioxide as a disinfectant," *JMedLife*, vol. 15, no. 3, pp. 313–318, Mar. 2022, doi: 10.25122/jml-2021-0180.
- [22] Y. Ran, C. Qingmin, and F. Maorun, "Chlorine Dioxide Generation Method and Its Action Mechanism for Removing Harmful Substances and Maintaining Quality Attributes of Agricultural Products," *Food Bioprocess Technol*, vol. 12, no. 7, pp. 1110–1122, Jul. 2019, doi: 10.1007/s11947-019-02279-x.
- [23] H. Bockhorn, A. Hornung, U. Hornung, and Djj. Schawaller, "Kinetic study on the thermal degradation of polypropylene and polyethylene," *Journal of Analytical and Applied Pyrolysis*, vol. 48, no. 2, pp. 93–109, 1999.
- [24] J. Chan and S. Balke, "The thermal degradation kinetics of polypropylene: Part III. Thermogravimetric analyses," *Polymer degradation and stability*, vol. 57, no. 2, pp. 135–149, 1997.
- [25] Z. Gao, T. Kaneko, I. Amasaki, and M. Nakada, "A kinetic study of thermal degradation of polypropylene," *Polymer Degradation and Stability*, vol. 80, no. 2, pp. 269–274, 2003.
- [26] Y. Lv, Y. Huang, M. Kong, and G. Li, "Improved thermal oxidation stability of polypropylene films in the presence of β-nucleating agent," *Polymer Testing*, vol. 32, no. 2, pp. 179–186, Apr. 2013, doi: 10.1016/j.polymertesting.2012.10.008.
- [27] V. Mylläri, T. Ruoko, and S. Syrjälä, "A comparison of rheology and FTIR in the study of polypropylene and polystyrene photodegradation," *J of Applied Polymer Sci*, vol. 132, no. 28, p. app.42246, Jul. 2015, doi: 10.1002/app.42246.

- [28] H. Nakatani *et al.*, "Studies of thermal oxidative degradation of polypropylene impact copolymer using the temperature rising elution fractionation method," *Polymer international*, vol. 56, no. 9, pp. 1152–1158, 2007.
- [29] D. G. Papageorgiou, D. N. Bikiaris, and K. Chrissafis, "Effect of crystalline structure of polypropylene random copolymers on mechanical properties and thermal degradation kinetics," *Thermochimica acta*, vol. 543, pp. 288–294, 2012.
- [30] M. S. Rabello and J. R. White, "Crystallization and melting behaviour of photodegraded polypropylene II. Re-crystallization of degraded molecules," *Polymer*, vol. 38, no. 26, pp. 6389–6399, Jan. 1997, doi: 10.1016/S0032-3861(97)00214-0.
- [31] C. Rouillon *et al.*, "Is carbonyl index a quantitative probe to monitor polypropylene photodegradation?," *Polymer Degradation and Stability*, vol. 128, pp. 200–208, Jun. 2016, doi: 10.1016/j.polymdegradstab.2015.12.011.
- [32] M. Mucha, "Dilatometric studies of isotactic polypropylene with different morphology before and after thermal degradation in air," *Colloid Polymer Sci*, vol. 259, no. 10, pp. 984– 989, Oct. 1981, doi: 10.1007/BF01558611.
- [33] M. Mucha and M. Kryszewski, "The effect of morphology on thermal stability of isotactic polypropylene in air," *Colloid Polymer Sci*, vol. 258, no. 6, pp. 743–752, Jun. 1980, doi: 10.1007/BF01384365.
- [34] P. Richters, "Initiation Process in the Oxidation of Polypropylene," *Macromolecules*, vol. 3, no. 2, pp. 262–264, Mar. 1970, doi: 10.1021/ma60014a027.
- [35] G. Grause, M.-F. Chien, and C. Inoue, "Changes during the weathering of polyolefins," *Polymer Degradation and Stability*, vol. 181, p. 109364, Nov. 2020, doi: 10.1016/j.polymdegradstab.2020.109364.

- [36] L. M. Smith, H. M. Aitken, and M. L. Coote, "The Fate of the Peroxyl Radical in Autoxidation: How Does Polymer Degradation Really Occur?," *Acc. Chem. Res.*, vol. 51, no. 9, pp. 2006–2013, Sep. 2018, doi: 10.1021/acs.accounts.8b00250.
- [37] G. Gryn'ova, J. L. Hodgson, and M. L. Coote, "Revising the mechanism of polymer autooxidation," *Org. Biomol. Chem.*, vol. 9, no. 2, pp. 480–490, 2011, doi: 10.1039/C0OB00596G.
- [38] A. Sarafpour and G. Pircheraghi, "The effect of carbon black on degradation of pipe grade black polyethylene in high concentration chlorine dioxide solutions," *Polymer Degradation and Stability*, vol. 230, p. 111031, Dec. 2024, doi: 10.1016/j.polymdegradstab.2024.111031.
- [39] M. Obadal, R. Čermák, and K. Stoklasa, "Tailoring of Three-Phase Crystalline Systems in Isotactic Poly(propylene)," *Macromol. Rapid Commun.*, vol. 26, no. 15, pp. 1253–1257, Aug. 2005, doi: 10.1002/marc.200500272.
- [40] A. T. Jones, J. M. Aizlewood, and D. R. Beckett, "Crystalline forms of isotactic polypropylene," *Macromolecular Chemistry and Physics*, 1964, doi: 10.1002/MACP.1964.020750113.
- [41] J. Karger-Kocsis, "Polypropylene : structure, blends and composites," 1995, doi: 10.1007/978-94-011-0521-7.
- [42] C. De Rosa, F. Auriemma, O. Ruiz De Ballesteros, L. Resconi, and I. Camurati,
 "Crystallization Behavior of Isotactic Propylene–Ethylene and Propylene–Butene
 Copolymers: Effect of Comonomers *versus* Stereodefects on Crystallization Properties of
 Isotactic Polypropylene," *Macromolecules*, vol. 40, no. 18, pp. 6600–6616, Sep. 2007, doi: 10.1021/ma070409+.

- [43] A. Turner-Jones, "Development of the γ-crystal form in random copolymers of propylene and their analysis by dsc and x-ray methods," *Polymer*, vol. 12, no. 8, pp. 487–508, Aug. 1971, doi: 10.1016/0032-3861(71)90031-0.
- [44] M. Van Drongelen, T. B. Van Erp, and G. W. M. Peters, "Quantification of non-isothermal, multi-phase crystallization of isotactic polypropylene: The influence of cooling rate and pressure," *Polymer*, vol. 53, no. 21, pp. 4758–4769, Sep. 2012, doi: 10.1016/j.polymer.2012.08.003.
- [45] E. Tarani, I. Arvanitidis, D. Christofilos, D. N. Bikiaris, K. Chrissafis, and G. Vourlias,
 "Calculation of the degree of crystallinity of HDPE/GNPs nanocomposites by using various experimental techniques: a comparative study," *J Mater Sci*, vol. 58, no. 4, pp. 1621–1639, Jan. 2023, doi: 10.1007/s10853-022-08125-4.
- [46] M. Mucha, "Rate of thermooxidation and polymer morphology," *Colloid & Polymer Sci*, vol. 264, no. 1, pp. 1–8, Jan. 1986, doi: 10.1007/BF01410302.