

## **Technical Data Sheet**

Product Name

SCGC™ MDPE

Product Grade

M600S

#### Product Typ

## SCGC™ MDPE

# **Product Description**

SCGC™ MDPE M600S is a black medium density polyethylene compound for geomembrane application which requires excellent compatibility and well-dispersed carbon black to provide excellent weathering and UV resistance.

## **Typical Application**

- Typical geomembrane application
- Landfill
- Pond liner
- Waste containment
- Liner for mining heap leach
- Tailing dams

### **Product Characteristics**

- Good mechanical properties
- Excellent compatibility
- Well-dispersed carbon black

### **International Compliance**

• Compliance with GRI GM13

## **Physical Properties**

Properties	Test Method	Typical Value	Unit
Melt Flow Rate at 190 °C and 2.16 kg	ASTM D 1238	0.20	g/10 min
Density	ASTM D 1505	0.939	g/cm³
Density (Compound)	ASTM D 1505	0.949	g/cm³
Carbon black content	ASTM D 4218	2.3	%wt
Tensile Strength at Yield	ASTM D 6693	35	kN/m
Elongation at Break	ASTM D 6693	870	%
Tear Resistance	ASTM D 1004	276	N
Puncture Resistance	ASTM D 4833	724	N
Stress Crack Resistance	ASTM D 5397	> 600	Hours
Oxidation Induction Time	ASTM D 3895	190	min
Standard OIT, Oven aging at 85°C ASTM D 5721	ASTM D 3895	70	%
(%Retained after 90 days)			
High pressure OIT, UV resistance ASTM D 7238 (%Retained after 1600 hours)	ASTM D 5885	87	%

Note:

- The given values are typical value measured on the product. Values herein are not to be constructed as a product specification.
- The given values are typical value measured on the product thickness average 2.0 mm with compressive mold specimen.

Thai Polyethylene Co., Ltd.

Page | 1

1 Siam Cement Road, Bangsue, Bangkok, 10800 Thailand E-mail: foodbev\_pkg@scg.com

Published: November 2024 **www.scgchemicals.com** 



## **Technical Data Sheet**

Product Name SCGC™ MDPE

Product Grade

**M600S** 

# SCGC™ MDPE

#### **Processing Guidelines**

The actual processing conditions depend on each machine type, product dimensions, thickness and environment. It is recommended to use a screw giving good melting and mixing without excessive shear. Generally, melt temperature range should be 180-220°C. It is also recommended to have proper drying before using in order to acquire good product performance. If preheating and/or drying is used, the suitable condition is 80-95°C, 1-2 hours.

#### **Product Technical Assistance**

For technical assistance or further information on this product or any other SCG Chemicals' products, contact your SCG Chemicals technical services at the address as specified below.

### **Product Available Form**

**Product Packaging** 

• Black pellet

• 750 kg big bag

#### **Storage**

- Store in original container in tidy according to the manual of Handling and Storage from Thai Polyethylene Co., Ltd.
- Product(s) should be stored in dry and dust free location at temperature below 50 °C and protected from direct sunlight and/or heat, well-ventilated area, away from incompatible materials and food and drink, as this may lead to quality deterioration, which results in odour generation and colour changes and can have negative effects on the physical properties of this product.
- Keep container tightly closed and sealed until ready for use. Containers that have been opened must be carefully resealed and kept upright to prevent leakage. Do not store in unlabelled containers. Use appropriate containment to avoid environmental contamination.
- The storage area should be stable and not be slopped.

#### Safety

- The product is not classified as a hazardous material.
- Please see our Material Safety Data Sheet for details on various aspects of safety, recovery, and disposal of the products; for more information, contact your SCG Chemicals technical services.

Thai Polyethylene Co., Ltd.

Page | 2

1 Siam Cement Road, Bangsue, Bangkok, 10800 Thailand E-mail: foodbev\_pkg@scg.com

Published: November 2024 www.scgchemicals.com



## **Technical Data Sheet**

Product Name

SCGC™ MDPE

**M600S** 

Product Grade

## SCGC™ MDPE

#### Recycling

- The product is suitable for recycling using modern methods of shredding and cleaning. In-house production waste should be kept clean to facilitate direct recycling.
- Please see our Material Safety Datasheet for details on various aspects of safety, recovery and disposal of the products; for more information, contact your SCG Chemicals technical services.

#### **Related Documents**

- The latest version of this document will be available at our website, www.scgchemicals.com, or can be obtained from the SCG Chemicals technical services.
- The following related documents are available on request, and represent various aspects on the usability, safety, recovery and disposal of the product.
  - Safety Data Sheet
  - Declaration of Compliance

#### **Disclaimer**

- The Applications specified herein is for reference only.
- It is customer's responsibilities to inspect and test the product for suitability of the customer's own use and purpose. The customer is responsible for appropriate, safe, legal use, processing and handling of the product.
- To the best of our knowledge, the information contained herein is accurate and reliable as of the date of publication. We however do not assume any liability whatsoever for the accuracy and completeness of the information contained herein.
- We make no warranties which extend beyond the description herein. Nothing herein shall constitute any implied warranty of merchantability or fitness for a particular purpose.
- No liability can be accepted in respect of the use of the product in conjunction with other materials. The information contained herein relates exclusively to the product when it is not used in conjunction with any third party's materials.

Thai Polyethylene Co., Ltd.

Page I 3

1 Siam Cement Road, Bangsue, Bangkok, 10800 Thailand E-mail: foodbev\_pkg@scg.com

Published: November 2024 www.scgchemicals.com